

**BEZ ÖZELLİKLERİ / FABRIC SPECIFICATION****PP 065 (11x11 membran)**

	<b>BİRİM UNIT</b>	<b>ÇÖZGÜ WARP</b>	<b>ATKI WEFT</b>	<b>STANDART STANDARD</b>
<b>İPLİK CİNSİ</b> <i>MATERIAL TYPE</i>		<b>PA 6.6</b>	<b>PA 6.6</b>	
<b>İPLİK TİPİ</b> <i>YARN CONSTRUCTION</i>	dtex	<b>940</b>	<b>940</b>	
<b>KOPMA YÜKÜ</b> <i>BREAKING STRENGTH</i>	min. Kg/cm	<b>70</b>	<b>70</b>	TS EN ISO 13934-1
<b>KOPMA UZAMASI</b> <i>ELONGATION AT BREAK</i>	%	<b>20 ± 3</b>	<b>28 ± 3</b>	TS EN ISO 13934-1
<b>ISIL BÜZÜLME</b> <i>SHRINKAGE (30' - 160 °)</i>	% max	<b>3</b>	<b>0,5</b>	ASTM D4974-04
<b>KRİMP</b> <i>CRIMP</i>	% min	-	-	TS 254 ISO 7211-3
<b>BEZ AĞIRLIĞI</b> <i>FABRIC WEIGHT</i>	gr/m <sup>2</sup>	<b>280 ± %3</b>		TS EN 12127
<b>BEZ KALINLIĞI</b> <i>FABRIC THICKNESS</i>	mm	<b>0,60 ± 0,10</b>		TS 7128 EN ISO 5084
<b>YAPIŞMA</b> <i>ADHESION</i>	min. Kg/cm	<b>7</b>		TS EN ISO 252
<b>RUTUBET</b> <i>HUMIDITY</i>	% max	<b>2</b>		TS 467
<b>DOKUMA TİPİ</b> <i>WEAVE</i>		<b>PLAIN</b>		

**Tüm değerler banyo edilmiş beze aittir / All values are related to RFL - Finished fabric**

**BEZ ÖZELLİKLERİ / FABRIC SPECIFICATION****PP 080 (9x9 membran)**

	<b>BİRİM UNIT</b>	<b>ÇÖZGÜ WARP</b>	<b>ATKI WEFT</b>	<b>STANDART STANDARD</b>
<b>İPLİK CİNSİ</b> <i>MATERIAL TYPE</i>		<b>PA 6.6</b>	<b>PA 6.6</b>	
<b>İPLİK TİPİ</b> <i>YARN CONSTRUCTION</i>	dtex	<b>1880</b>	<b>1880</b>	
<b>KOPMA YÜKÜ</b> <i>BREAKING STRENGTH</i>	min. Kg/cm	<b>130</b>	<b>130</b>	TS EN ISO 13934-1
<b>KOPMA UZAMASI</b> <i>ELONGATION AT BREAK</i>	%	<b>22 ± 3</b>	<b>35 ± 3</b>	TS EN ISO 13934-1
<b>ISIL BÜZÜLME</b> <i>SHRINKAGE (30' - 160 °)</i>	% max	<b>2</b>	<b>0,5</b>	ASTM D4974-04
<b>KRİMP</b> <i>CRIMP</i>	% min	-	-	TS 254 ISO 7211-3
<b>BEZ AĞIRLIĞI</b> <i>FABRIC WEIGHT</i>	gr/m <sup>2</sup>	<b>435 ± %3</b>		TS EN 12127
<b>BEZ KALINLIĞI</b> <i>FABRIC THICKNESS</i>	mm	<b>0,90 ± 0,05</b>		TS 7128 EN ISO 5084
<b>YAPIŞMA</b> <i>ADHESION</i>	min. Kg/cm	<b>7</b>		TS EN ISO 252
<b>RUTUBET</b> <i>HUMIDITY</i>	% max	<b>2</b>		TS 467
<b>DOKUMA TİPİ</b> <i>WEAVE</i>		<b>PLAIN</b>		

**Tüm değerler banyo edilmiş beze aittir / All values are related to RFL - Finished fabric**

**BEZ ÖZELLİKLERİ / FABRIC SPECIFICATION****PP LINER (ara bezi)**

	<b>BİRİM UNIT</b>	<b>ÇÖZGÜ WARP</b>	<b>ATKI WEFT</b>	<b>STANDART STANDARD</b>
<b>İPLİK CİNSİ MATERIAL TYPE</b>		<b>PP MULTI</b>	<b>PP MONO</b>	
<b>İPLİK TİPİ YARN CONSTRUCTION</b>	dtex	<b>1100</b>	<b>450</b>	
<b>KOPMA YÜKÜ BREAKING STRENGTH</b>	min. Kg/cm	<b>80</b>	<b>22</b>	TS EN ISO 13934-1
<b>KOPMA UZAMASI ELONGATION AT BREAK</b>	%	<b>40 ± 3</b>	<b>20 ± 3</b>	TS EN ISO 13934-1
<b>ISIL BÜZÜLME SHRINKAGE (30' - 160 °)</b>	% max	-	-	ASTM D4974-04
<b>KRİMP CRIMP</b>	% min	-	-	TS 254 ISO 7211-3
<b>BEZ AĞIRLIĞI FABRIC WEIGHT</b>	gr/m <sup>2</sup>	<b>230 ± %3</b>		TS EN 12127
<b>BEZ KALINLIĞI FABRIC THICKNESS</b>	mm	<b>0,66 ± 0,05</b>		TS 7128 EN ISO 5084
<b>YAPIŞMA ADHESION</b>	min. Kg/cm	-		TS EN ISO 252
<b>RUTUBET HUMIDITY</b>	% max	-		TS 467
<b>DOKUMA TİPİ WEAVE</b>		<b>PLAIN</b>		

**BEZ ÖZELLİKLERİ / FABRIC SPECIFICATION****PP LINER - S (ara bezi)**

	<b>BİRİM UNIT</b>	<b>ÇÖZGÜ WARP</b>	<b>ATKI WEFT</b>	<b>STANDART STANDARD</b>
<b>İPLİK CİNSİ</b> <i>MATERIAL TYPE</i>		<b>PP MULTI</b>	<b>PP MULTI</b>	
<b>İPLİK TİPİ</b> <i>YARN CONSTRUCTION</i>	dtex	<b>1100</b>	<b>1100</b>	
<b>KOPMA YÜKÜ</b> <i>BREAKING STRENGTH</i>	min. Kg/cm	<b>90</b>	<b>45</b>	TS EN ISO 13934-1
<b>KOPMA UZAMASI</b> <i>ELONGATION AT BREAK</i>	%	<b>40 ± 3</b>	<b>20 ± 3</b>	TS EN ISO 13934-1
<b>ISIL BÜZÜLME</b> <i>SHRINKAGE (30' - 160 °)</i>	% max	-	-	ASTM D4974-04
<b>KRİMP</b> <i>CRIMP</i>	% min	-	-	TS 254 ISO 7211-3
<b>BEZ AĞIRLIĞI</b> <i>FABRIC WEIGHT</i>	gr/m <sup>2</sup>	<b>250 ± %3</b>		TS EN 12127
<b>BEZ KALINLIĞI</b> <i>FABRIC THICKNESS</i>	mm	<b>0,70 ± 0,05</b>		TS 7128 EN ISO 5084
<b>YAPIŞMA</b> <i>ADHESION</i>	min. Kg/cm	-		TS EN ISO 252
<b>RUTUBET</b> <i>HUMIDITY</i>	% max	-		TS 467
<b>DOKUMA TİPİ</b> <i>WEAVE</i>		<b>PLAIN</b>		